(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



I MARIN ANNON NA ARANA MARIN BARNI BARNI BARNI KAN KAN BARNI BARNI BARNI BARNI BARNI BARNI BARNI BARNI BARNI B

(43) International Publication Date 31 March 2005 (31.03.2005)

PCT

(10) International Publication Number WO 2005/028097 A1

(51) International Patent Classification⁷: C08F 2/01

B01J 19/18,

(21) International Application Number:

PCT/EP2004/010375

(22) International Filing Date:

16 September 2004 (16.09.2004)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: 103 44 500.5 24 September 2003 (24.09.2003) DE 60/529,037 12 December 2003 (12.12.2003) US

(71) Applicant (for all designated States except US): BASELL POLYOLEFINE GMBH [DE/DE]; Brühler Strasse 60, D-50389 Wesseling (DE). (72) Inventors; and


(75) Inventors/Applicants (for US only): MIHAN, Shahram [IR/DE]; Am Eichwald 18, D-65812 Bad Soden (DE). GSELLA, Wolfgang [DE/DE]; Bergstr. 34, D-50999 Köln (DE). KÖLLE, Peter [DE/DE]; Kirschblütenweg 7, D-50996 Köln-Rodenkirchen (DE). WULFF-DÖRING, Joachim [DE/DE]; Hanns-Fey-Str. 4, D-67227 Frankenthal (DE).

(74) Agent: BASELL POLYOLEFINE GMBH; Intellectual Property - F 206, Carl-Bosch-Str. 38, D-67056 Ludwigshafen (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,

[Continued on next page]

(54) Title: LOOP REACTOR WITH VARYING DIAMETER FOR OLEFIN POLYMERIZATION



(57) Abstract: Process for polymerizing at least one olefinic monomer in a loop reactor at from 20 to 150°C, but below the melting point of the polymer to be formed, and a pressure of from 5 to 100 bar, where the polymer formed is present in a suspension in a liquid or supercritical suspension medium and this suspension is circulated by means of an axial pump, wherein the loop reactor comprises a cyclic reactor tube whose diameter varies by at least 10%, based on the predominant reactor tube diameter, and in which there is at least one widening and narrowing in a region other than that of the axial pump.



PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,

SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

of inventorship (Rule 4.17(iv)) for US only

Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.